

PUB-NO: JP410088075A

DOCUMENT-IDENTIFIER: JP 10088075 A

TITLE: PRIMER FOR BONDING SYNTHETIC RESIN AND BONDING METHOD THEREWITH

PUBN-DATE: April 7, 1998

INVENTOR-INFORMATION:

NAME	COUNTRY
NOGUCHI, KENJI	
OHASHI, KOICHI	
INT-CL (IPC): C09J 5/02; C09J 161/06; C09J 163/00	

ABSTRACT:

PROBLEM TO BE SOLVED: To obtain a bonding method whereby troublesome pretreatment works are cut down and a high adhesive strength can be obtd. by using a primer contg. a specific compd. and an org. solvent.

SOLUTION: This primer contains a compd. represented by the formula (R is II, halogen, or a 1-10C linear or branched aliph. hydrocarbon group; X and Y are each halogen or hydroxyl provided they are not simultaneously hydroxyl; and n is 0-30), and this method uses the primer. In bonding a nylon resin with an epoxy resin adhesive, the surface of the nylon resin is treated with a primer contg, the compd. represented by the formula and the solvent before being bonded. The compd. is produced by condensing a phenol and formaldehyde in the presence of an alkali catalyst (e.g. caustic soda) and halogenating terminal methylol groups of the resultant resol resin with a halogenating agent. The solvent is pref. ethyl acetate or tetrahydrofuran(THF).

COPYRIGHT: (C)1998,JP0